

Magnetic polarons in weakly doped high- T_c superconductors.

E. M. Hankiewicz, R. Buczko, and Z. Wilamowski

*Institute of Physics, Polish Academy of Sciences,
al. Lotników 32/46, PL 02-668 Warsaw Poland*

We consider a spin Hamiltonian describing d - d exchange interactions between localized spins d of a finite antiferromagnet as well as p - d interactions between a conducting hole (p) and localized spins. The spin Hamiltonian is solved numerically with use of Lanczos method of diagonalization. We conclude that p - d exchange interaction leads to localization of magnetic polarons. Quantum fluctuations of the antiferromagnet strengthen this effect and make the formation of polarons localized in one site possible even for weak p - d coupling. Total energy calculations, including the kinetic energy, do not change essentially the phase diagram of magnetic polarons formation. For parameters reasonable for high- T_c superconductors either a polaron localized on one lattice cell or a small ferron can form. For reasonable values of the dielectric function and p - d coupling, the contributions of magnetic and phonon terms in the formation of a polaron in weakly doped high- T_c materials are comparable.

PACS numbers: 74.72.-h, 74.20.-z, 71.38.-k

I. INTRODUCTION

The role of electron phonon and spin exchange in the formation of polarons, bi-polarons and stripes in CuO_2 based high- T_c materials has been a matter of extensive discussion from the very moment high- T_c superconductors were discovered. Experimental observations of the anomalous isotope effect^{1,2} could indicate the role of phonon interactions in the formation of the superconducting state. On the other hand, angularly resolved photoemission³ (ARPES), transport⁴ and tunneling microscopy measurements⁵ show d -symmetry of the order parameter indicating an important role of exchange. Although some authors underline the role of both mechanisms⁶, the solution of full Hamiltonian is complicated and these contributions are usually calculated separately.

The concept of the phonon polaron was introduced by Pekar⁷ and Fröhlich^{8,9} decades ago and was adopted to high- T_c superconductors by Alexandrov and Mott¹⁰. The energy of phonon coupling for high- T_c is estimated to be of the order of a fraction of eV. In another work, Alexandrov¹¹ proposed that the narrowing of d -electron band by the polaron effect and the formation of phonon bipolarons increases the critical temperature to $T_c \approx 100$ K. However, because of the dominant contribution of d -symmetry to the order parameter of high- T_c superconductors, exchange interactions are the most often considered ones recently. The modeling of such interactions is difficult because it is necessary to include the role of conducting (p) holes as well as localized (d) electrons.

In the case of weak p - d couplings a linear response of the antiferromagnet (AF) can be assumed. Hence, a phenomenological model of magnetic susceptibility

introduced by Millis, Monien, Pines¹² (MMP) can be used.

Zhang and Rice¹³, in turn, describe the case of strong hybridization between the $3d$ states of Cu and $2p$ states of O. When the hybridization is much greater than the kinetic energy of the carriers, it is possible to limit the description to the ground singlet state, and in such a case a one band model can be used. This model (called t - J) is at present the most often used to describe the cuprate superconductors (for a review see¹⁴). Unfortunately, different techniques of approximations lead sometimes to contradictory solutions of t - J , as it is in the case of the stripe formation^{15,16}. Also, the dynamics of spin polaron in the framework of t - J model was extensively investigated by many authors^{17,18,19,20,21,22}.

However, the spin-fermion model^{23,24,25,26,27,28,29,30}, which treats separately the spin of p -carrier and d -localized spins, seems to be the most appropriate for the case of intermediate p - d coupling typical for high- T_c superconductors. Most papers treat the p - d interaction as a Kondo exchange. Such an approach allows to show the tendency of cuprates to stripe phase formation²³ or d -wave pairing^{25,26}. Recently, Bala et al.^{29,30} extended the spin-fermion model starting from the three band Hubbard model. They introduced p - d coupling, which is much more complicated than Kondo one, i.e. some exchange couplings between Cu ion and two neighboring oxygen atoms appear. They have considered the formation of magnetic polaron in such a model^{29,30}. They identified all the spectrum of energy states of Zhang-Rice polaron³⁰ in ARPES experiments³¹. They found a solution using self-consistent Born approximation (SCBA). However, a comparison of SCBA and exact diagonalization techniques for spin-fermion model has not been carried out yet.

The present paper reports for the first time on calculations of a simple spin-fermion model with exact diagonalization technique for spin Hamiltonian. It broadens the possible range of solutions. The spin-fermion model allows to investigate the cases of strong and intermediate p - d coupling. Thus a comparison of the phonon and magnetic contributions to the formation of a polaron in weakly doped high- T_c superconductors for a wide range of parameters is possible. The magnetic exchange interactions are calculated strictly while the phonon contribution is evaluated in the framework of the Fröhlich theory^{8,9,10}.

In Section 2, we describe the Hamiltonian and the method of finding the ground and excited states of the system. In Section 3, the exchange spin interactions are analyzed. In Section 4, we construct and analyze phase diagram for the formation of different magnetic polarons. In Section 5, we compare the energies of phonon and magnetic polarons. A summary is given in Section 6.

II. MODEL

We study a system which consists of spins localized on the d -shells and mobile p -like holes. The localized spins are treated within the quantum antiferromagnet model, i.e. none of the Neel sublattices are chosen a priori. We consider finite one- (1D) and two- dimensional (2D) clusters as well as the infinite system. The latter is simulated using periodic boundary conditions (PBC) and an extrapolation to an infinite size. The spin interactions in the system and the kinetic energy of the p hole is described by the Hamiltonian:

$$H = 2J_{dd} \sum_{\langle i,j \rangle} \mathbf{S}_i \mathbf{S}_j + \frac{1}{2} J_{pd} \sum_{i,\alpha,\beta} \mathbf{S}_i c_{i\alpha}^+ \boldsymbol{\sigma}_{\alpha\beta} c_{i\beta} + t_{ij} \sum_{i,j,\alpha} c_{i\alpha}^+ c_{j\alpha}, \quad (1)$$

where $\mathbf{S}_i$ is the effective spin of the nine core d -electrons ($3d^9$), the summation was taken under the pairs of neighboring spins $\langle i, j \rangle$, $\boldsymbol{\sigma}_{\alpha\beta}$ are the Pauli matrices of the carrier spin $\mathbf{s}$, J_{pd} is the Kondo parameter normalized to the volume of elementary cell, J_{dd} is the exchange integral between d - d spins, t_{ij} is the hopping matrix element to the neighbor, $c_{i\alpha}^+$, $c_{i\alpha}$ are the operators of creation and annihilation of a hole on the i -th site, with the projection of spin 1/2 on the quantization axis equal α respectively. We look for the eigenstates of the Hamiltonian (1) in the form of the product of the orbital wave vector, Ψ , and the spin state vector of local and carrier spins X_S :

$$\Psi \cdot X_S. \quad (2)$$

In the space of the single hole occupation at antiferromagnet (AF) sites $i = 1, \dots, N$

$$\Psi = \sum_i \varphi(i) u_i, \quad (3)$$

where $u_i = |0, 0, \dots, 1, 0, 0, \dots\rangle$ is the occupation vector of the hole at i -th site and $\varphi(i)$ is the corresponding probability amplitude. We use the variational method of solving the eigenproblem. We treat Ψ as the trial function, which is normalized by the condition:

$$\sum_i^N |\varphi(i)|^2 = 1. \quad (4)$$

For Ψ given by Eq. (2) the diagonalization of the kinetic and exchange terms of Hamiltonian (1) can be done separately.

$$H' = \langle \Psi | H | \Psi \rangle = T + H_s. \quad (5)$$

The kinetic energy, T , does not depend on the spin state X_S and can be easily evaluated from the probability amplitude of the carrier $\varphi(i)$:

$$T = z|t_1| - 2|t_1| \sum_{\langle i,j \rangle} \varphi(i)\varphi(j), \quad (6)$$

if only the hopping to the nearest neighbors (NN), t_1 is considered, and z is the number of NN. The term $z|t_1|$ has been added to have zero kinetic energy for fully delocalized states. Calculations of the exchange energy need diagonalization of the spin Hamiltonian:

$$H_s = 2J_{dd} \sum_{\langle i,j \rangle} \mathbf{S}_i \mathbf{S}_j + \sum_i j_{pd}(i) \mathbf{S}_i \mathbf{s}. \quad (7)$$

Here $\mathbf{s}$ is the spin operator of the carrier spin and the p - d exchange integrals are given by

$$j_{pd}(i) = J_{pd} |\varphi(i)|^2. \quad (8)$$

We use Lanczos method of diagonalization of the spin Hamiltonian (7). Diagonalization of matrices for AF cluster with $N \leq 20$ is possible with the PC computer. For larger clusters the calculation time increases rapidly.

A detailed study of quantum coupling between spins within the polaron in an AF medium is the main goal of the paper. We focus our analysis on the gain E_{ex} of the spin exchange energy. E_{ex} is the difference between the energy of the ground state of the unperturbed AF E_{dd}^0

(when $J_{pd} = 0$) and the exchange energy of the whole system when the carrier is coupled to AF $E_{dd} + E_{pd}$, i.e.

$$E_{ex} = E_{dd}^0 - (E_{dd} + E_{pd}). \quad (9)$$

In this way, we analyze the zero temperature case only. We found that for a weak p - d exchange the gain E_{ex} is a half of the p - d coupling energy, $E_{ex} = -E_{pd}/2$.

The Hamiltonian includes neither effects of external magnetic field nor any other terms which could lead to the symmetry breaking and to the formation of Neel sublattices. As a consequence, the mean values of the magnetic moments of each spin of this system are exactly equal zero. Because of this, we describe the spin structure of the antiferromagnetic polarons (AFP) and the mechanism of the magnetic polaron formation by means of correlators between spins of AF $\langle \mathbf{S}_i \mathbf{S}_j \rangle$ and between the AF spin and that of an additional hole $\langle \mathbf{s} \mathbf{S}_i \rangle$:

$$\langle \mathbf{s} \mathbf{S}_i \rangle = \langle X_S | \mathbf{s} \mathbf{S}_i | X_S \rangle. \quad (10)$$

The assumption that the wave function can be described by Eq. 2 is simplified. In general, the total wave function is a linear combination of wave functions given by Eq. 2. In particular, because polarons localized on two Neel sublattices are equivalent, at least the combination of the pair of such states should be considered. This problem is discussed in section III G.

Hamiltonian (1) does not contain a phonon term. In general, the coupling of the carrier to the lattice polarization and the exchange interactions act together to form the polaron. The phonon term is treated in Section 5 within the simplest possible approach. It is calculated from Fröhlich interaction with optical phonons. It is known¹⁰ that in the range of parameters typical for high- T_c superconductors small phonon polarons are formed. Their energy is given by:

$$E_{ph} \approx \frac{q_D e^2}{\pi \kappa}, \quad (11)$$

where $q_D = \left(\frac{6\pi^2}{V} \right)^{1/3}$ is the Debye momentum, $\frac{1}{\kappa} = \frac{1}{\epsilon} - \frac{1}{\epsilon_0}$; ϵ , ϵ_0 are dynamic and static dielectric constants respectively, and e is the electron charge.

III. SPIN STRUCTURE OF MAGNETIC POLARONS

We examine various types of trial functions φ . Depending on the size and shape of the carrier distribution, $|\varphi|^2$ (Fig. 1), as well as on the value of exchange




FIG. 1: The exchange energy gain, E_{ex} , obtained for a Gaussian trial function is presented as a function of polaron radius r'_p , for 1D open chain (crosses), for 1D chain with PBC (open squares) and for a 4×4 square with PBC (open stars). Open triangles show $E_{ex}(r'_p)$ for a comb-like carrier trial function (see Eq. 14) and 1D AF chain of 16 spins. In the inset the extrapolation of E_{ex} to infinite AF 1D cluster is shown by filled triangles, squares and circles for $r'_p = 0.75a_0$, $r'_p = 1.5a_0$ and $r'_p = 3a_0$ respectively, where a_0 is a lattice constant. In the icons arrows show the correlators between the carrier spin and spins of AF for a small AFP ($r'_p = 0$), medium AFP ($r'_p = 0.6a_0$) and large AFP ($r'_p = 1.4a_0$). For a large AFP, the arrow size is multiplied 30 times for clarity. Solid curves show trial functions.

constants (Fig. 2) various types of magnetic polarons with very different spin structures can be found.

A. Large AFP. Its size r'_p is much greater than the lattice constant a_0 and the antiferromagnetic correlation range ξ . Thus, it can be described within the theory of the linear response. For very large polarons the local magnetization $M(\mathbf{r})$ becomes proportional to the local carrier density¹².

B. Medium AFP. Its size r'_p is comparable or smaller than ξ , but bigger than $0.5a_0$ (see Fig. 1). The induced polarization is of staggered character, and the carrier interacts with few local spins of different orientation.

C. Small AFP It is localized within a single elementary cell. For very strong p - d coupling it corresponds to the Zhang-Rice polaron.

D. Ferron. It forms when the p - d exchange is strong enough to break AF bonds and to induce a local magnetic moment³².

E. Comb like AFP It is the case when the carrier is distributed on one Neel sublattice only. The staggered polarization is the dominant response of the AF medium^{25,33}.

The clear difference between AFP of different sizes




FIG. 2: The exchange energy gain, E_{ex} , from formation of different magnetic polarons as a function of J'_{pd} . E_{ex} for a small AFP were obtained for a 1D chain with PBC (open circles) and for a 2D 4×4 square with PBC (filled circles). E_{ex} for a trial function evenly distributed on all AF spins are shown by open and filled squares for a 1D chain with PBC and 2D 4×4 with PBC respectively. Results for a trial function distributed on two neighbor AF spins and a 1D chain with PBC are drawn by filled triangles. The dashed lines show quadratic and linear dependencies of E_{ex} on J'_{pd} . The dotted line emphasizes superquadratic dependence of $E_{ex}(J'_{pd})$. The inset shows $E_{ex}(J'_{pd})$ for a small AFP.

is seen in Fig. 1, where the energy gain, E_{ex} , is plotted as a function of the polaron size r'_p . Gaussian trial function $|\varphi(i)|^2 = A \exp\left[-\frac{(\mathbf{r}_i - \mathbf{r}_0)^2}{2r_p'^2}\right]$, where A is a normalization factor and $\mathbf{r}_i - \mathbf{r}_0$ is the distance from central spin, was used to calculate almost all curves. The curve plotted by triangles, however, was calculated using another trial function, and it represents the formation of a comb-like AFP. It will be discussed in part III E.

The calculations were performed for weak p - d coupling for 1D and 2D AF clusters. The number of AF bonds has been assumed to be twice as big for 2D as for a 1D cluster, where the number of ligands is two times smaller. To compare the results for 1D and 2D clusters we introduce the following quantity, $J'_{pd} = J_{pd}/(2zJ_{dd})$, which describes the ratio of p - d to d - d coupling normalized by the number of AF bonds, $2z$. Ratio of the p - d to the d - d exchange energies defined this way is the same for 1D and 2D AF clusters. Moreover, $J'_{pd} \ll 1$ describes the range of weak p - d coupling, while $J'_{pd} > 1$ that of strong p - d coupling, independent of the dimension of the AF cluster. J'_{pd} is set 1/4 in Fig. 1. Here the small AFP corresponds to $r'_p < 0.4a_o$, medium to $0.4a_o < r'_p < a_o$, and large to $r'_p > a_o$. The dependence of E_{ex} on the chain length is shown in the inset. The

linear dependence of the E_{ex} on the inverse AF cluster size $1/N$ makes the extrapolation to an infinite chain possible. The extrapolated values of E_{ex} are shown by full circles in Fig. 1.

The results of calculations for small and medium AFP in the 1D case are reasonable even without extrapolation to infinite clusters. Because of that, we assume that also for the 2D case the energy of small and medium polarons can be found with reasonable accuracy. Unfortunately, because of computational limitations, we can not carry out full extrapolation for large AFP in 2D clusters.

A comparison of numerical results for open chains and chains with PBC shows that the use of PBC does not lead to an improvement of the convergence of numerical results with the cluster size. In part, this is an effect of the normalization condition given by (Eq. 4) and of specific properties of the dangling spins at the cluster border.

A. Large AFP

The numerical results, with the characteristic dependence of the E_{ex} decreasing as $1/r'_p$ for 1D AF, can be approximated by an analytical solution in which the magnetic susceptibility of AF is described by two phenomenological parameters. The analytical solution gives a better description of large AFP while the comparison with the numerical results allows to explain the physical meaning of the phenomenological parameters.

For simplicity in the analytical approximation, we use an exponential distribution of carrier density, $|\varphi(\mathbf{r}')|^2 = \frac{1}{2r_p} \exp(-|\mathbf{r}' - \mathbf{r}_0|/r_p)$, where $\mathbf{r}_0$ is the center of the density distribution and $r_p^2 = 2r_p'^2$. We assume that the susceptibility in wave vector space can be described by the phenomenological formula introduced in the MMP model¹², $\chi(\mathbf{q}) = \chi_{q_0} \frac{1}{1 + (\mathbf{q} - \mathbf{q}_0)^2 \xi^2}$, where $\mathbf{q}$ is the wave vector, $q_0 = \pi/a_0$ and corresponds to the staggered magnetization. The phenomenological parameters χ_{q_0} and ξ describe the staggered magnetic susceptibility and the spin correlation length, respectively. An effective field corresponding to $\varphi(\mathbf{r}')$ is $H_{eff}(\mathbf{r}') = \frac{J_{pd}a_0}{4g\mu_B r_p} \exp(-|\mathbf{r}' - \mathbf{r}_0|/r_p)$. Within the model of continuous media, an effective field acting at a point $\mathbf{r}'$ results in magnetization $M(\mathbf{r}) = \int d\mathbf{r}' \chi(\mathbf{r} - \mathbf{r}') H_{eff}(\mathbf{r}')$ at the point $\mathbf{r}$. Such an approach takes into account the non-local effects of correlated systems but neglects the atomic structure of AF. For large AFP, i.e. for $r_p \gg \xi$, $M(\mathbf{r})$ takes a simple form:

$$M(\mathbf{r}) = \frac{J_{pd}a_0\chi_{q_0}}{16\pi^2 g\mu_B \xi^2} \frac{1}{q_0^2 r_p} \exp\left(-\frac{|\mathbf{r} - \mathbf{r}_0|}{r_p}\right). \quad (12)$$

Thus $M(\mathbf{r})$ induced by a large AFP is smooth and described by the same spatial dependence as the carrier density. In the icon in Fig. 1, the correlators between the carrier spin, $\mathbf{s}$ and the consecutive local spins, $\mathbf{S}_i$, for a large AFP are presented. They also show that for a large AFP the induced magnetization is smooth and proportional to the carrier density. In that sense the analytical solution is equivalent to the numerical one. $E_{ex} = 1/2E_{pd}$ for a large AFP and it takes a simple form:

$$E_{ex} = \frac{(J_{pd}a_0)^2 \chi_{q_0}}{256\pi^2 (g\mu_B)^2 \xi^2 q_0^2 r_p}. \quad (13)$$

The absolute value of E_{ex} and its dependence on the d - d exchange and on the correlation length cannot be analyzed within the discussed phenomenological approach. However, an evaluation of E_{ex} can be done by numerical calculations. If one attributes the correlation length to the cluster size, then the comparison of Eq. 13 with the numerical result, showing that the energy gain is almost independent of the chain length (see inset to Fig. 1), leads to the conclusion that $\chi_{q_0} \propto \xi^2/J_{dd}$ for a large 1D polaron. We found out that the character of the obtained dependencies does not change if a Gaussian trial function was applied.

In the 2D case, the results of numerical integration for large AFP in a 2D system are characterized by a faster decrease of E_{ex} with the polaron size in comparison to the 1D case. The energy scales with $1/r_p^2$ instead of $1/r_p$.

To summarize, the large AFP is characterized by a smooth magnetization of the antiferromagnet, proportional to the carrier density. Because for a 2D polaron E_{ex} and the kinetic energies scale with the inverse square of the polaron size, two scenarios are possible: (i) no polaron can be formed when $T > E_{ex}$, or, in the opposite case, (ii) the minimum of the total energy occurs for the polaron radius tending to zero (see also Fig. 6). In that case, however, it is no longer a large polaron and a different approximation should be considered.

B. Medium AFP

As it is shown in Fig. 1, with a decrease of r'_p , E_{ex} does not follow the $1/r'_p$ dependence, but for $r'_p < a_0$ a sharp increase of E_{ex} is seen. For 1D the increase of $E_{ex} \sim 10$, as compared to the extrapolated $1/r'_p$ dependence, and for 2D is even bigger. The rapid increase of E_{ex} shows that the medium AFP has a tendency to localization. The decrease of r'_p is also accompanied by a change of the character of induced magnetization in the AF medium. As it is shown by icons in Fig. 1, nu-




FIG. 3: (a) The correlator, $|\langle \mathbf{sS}_0 \rangle|$, between the carrier spin, and AF spin on which the carrier is localized as a function of J'_{pd} for 1D chain with PBC (filled circles) and 2D 4×4 square with PBC (open stars). Icons show the correlators between the carrier spin, $\mathbf{s}$, and consecutive d spins of AF chain for corresponding J'_{pd} . (b) The z -component of carrier spin, $\mathbf{s}_z$, of central spin $\mathbf{S}_{0z}$, as well as the sum of AF spins $\sum_i \mathbf{S}_{iz}$ are shown for an open chain of 16 spins as a function of J'_{pd} . (c) The correlator between the spin on which the polaron is acting and the NN (filled circles) and the NNN spin (open squares) for a chain of 16 spins. The correlator between the spin on which the polaron is acting and the NN spin for a 2D 4×4 square with PBC is presented by stars.

merical calculations predict a smooth magnetization for $r'_p \geq a_0$ but a staggered one for $r'_p < a_0$.

For a weak p - d coupling, E_{ex} increases with the square of J'_{pd} (see filled triangles in Fig. 2). However, calculations show that for $J'_{pd} > 1$ a more complex mechanism occurs. The AF bonds broke and a ferronlike polaron forms. The details are described in part IIID.

C. Small AFP

When the polaron radius becomes comparable to the size of the elementary cell, E_{ex} saturates. The plateau in Fig. 1 corresponds to the case when the polaron is localized in a single elementary cell, i.e. $r'_p < a_0$. The numerical results weakly depend on the size of AF cluster and on boundary conditions. The magnetization induced by the small AFP is similar to that of the medium AFP, as it is shown by icons in Fig. 1.

A dependence of the numerically calculated E_{ex} on the normalized ratio p - d to d - d exchange J'_{pd} is shown by circles in Fig. 2. There is no considerable difference between 1D and 2D cases. For a weak p - d coupling

$E_{ex} \propto J_{pd}^2$. The upper limit of this quadratic dependence corresponds to the case when the p - d coupling is equal to the d - d exchange. For higher J_{pd}' the energy increases linearly.

The correlator $\langle \mathbf{s}\mathbf{S}_0 \rangle$ between the carrier spin, $\mathbf{s}$, and AF spin on which the carrier is localized, $\mathbf{S}_0$, is shown in Fig. 3a. In the range of weak p - d couplings, the magnetization of the local spin, as seen by the carrier spin, $\langle \mathbf{s}\mathbf{S}_0 \rangle$, increases linearly and saturates for the strong J_{pd}' . This corresponds to quadratic and linear dependence of E_{ex} versus J_{pd}' , respectively. For a strong J_{pd}' , the correlator $\langle \mathbf{s}\mathbf{S}_0 \rangle = -3/4$ that means AF spin is compensated by the spin of a carrier.

The icons in Fig. 3a show the correlators between the carrier spin $\mathbf{s}$ and the consecutive d spins of AF chain for different J_{pd}' . It is seen that a small polaron induces a staggered magnetization within the AF correlation range, ξ . But the amplitude of $\langle \mathbf{s}\mathbf{S}_0 \rangle$ varies with J_{pd}' . The increase of the correlator $|\langle \mathbf{s}\mathbf{S}_0 \rangle|$ is accompanied by a reduction of the correlators between the carrier spin and other d spins. Also, the correlator of the spin $\mathbf{S}_0$ with neighboring spins $\mathbf{S}_i$, $\langle \mathbf{S}_0\mathbf{S}_i \rangle$, decreases with J_{pd}' increase. The dependence of correlator for NN and the next nearest neighbor (NNN) are shown in Fig. 3c. The correlators are not affected by the presence of a weak polaron, but for stronger J_{pd}' they decrease as $1/J_{pd}'$.

The ground state of a system consisting of a carrier with $s = 1/2$ and an AF cluster of an even number of local spins is a spin doublet, for any J_{pd}' . However, depending on the value of J_{pd}' , the magnetic moment can be transferred from the carrier to the system of local spins. For a non-interacting spin $\mathbf{s}$, or for a very weak p - d coupling, the carrier spin has a magnetic moment while the total moment of localized spins is zero. In Fig. 3b the z -component of the carrier spin, s_z , the local spin S_{0z} and the sum of all local spins $\sum_i S_{iz}$ are plotted as a function of J_{pd}' . To distinguish the z -direction, we put a small magnetic field which does not perturb the spin structure of polaron. With an increase of J_{pd}' the magnetic moment is transferred from the carrier to the local spins. For a very strong p - d coupling, the moment of local spins $\sum_i S_{iz}$ saturates at value $1/2$. At the same time, the moment of carrier spin and of the local spin, vanish. The magnetic moments of the local spins, $\sum_i S_{iz}$, are distributed in a staggered way among the whole cluster. In the limit of strong p - d coupling, $J_{pd}' \gg 1$ the small polaron is equivalent to the Zhang-Rice (ZR) one. Here the spins, $\mathbf{s}$ and $\mathbf{S}_0$, are compensated and form a local singlet state, not coupled to other local spins, $\mathbf{S}_i$ (see Fig. 3c and the icon in Fig. 3a.). On the other hand, the formation of a central pair of compensated spins is accompanied by a transfer of the magnetic moment to the neighboring local spins and formation of staggered $M(\mathbf{r})$ around the central

cell. Such an effect was described in details, for example in³⁴. The reconstruction of AF bonds in the vicinity of the small AFP is driven by a gain of d - d exchange energy. It is of the order of J_{dd} . It is a small contribution to the whole energy of the ZR polaron but becomes important for $J_{pd}' \cong 1$. Moreover, the reconstruction of the AF environment should be taken into account when interactions between separate polarons are discussed.

To summarize, the small AFP in the range of intermediate p - d coupling (typical for high- T_c superconductors) is not equivalent to the ZR polaron. The carrier spin is also partially correlated with AF spins in the vicinity of local singlet.

D. Ferron

As it is shown in Fig. 1, E_{ex} for a weak p - d coupling decreases with an increase of the polaron size. For big J_{pd}' , however, some new effects occur. As it is shown in Fig. 2, for a weak polaron evenly localized on two d -spins antiferromagnetically correlated E_{ex} is smaller by a factor ~ 80 than in the case of a small AFP. With an increase of J_{pd}' , instead of the expected saturation, a faster increase of E_{ex} for such a polaron occurs.

An even more pronounced effect is seen for a homogeneously distributed carrier density. As it is shown by squares in Fig. 2, E_{ex} for a weak p - d coupling is practically zero but sharply increases for $J_{pd}' \simeq 2$. Moreover, a further increase of J_{pd}' is accompanied with a step-like increase of E_{ex} . Studies of the spin structure show that this critical behavior is caused by a breakdown of the AF bonds and the formation of a magnetic moment in the antiferromagnetic medium. Such a magnetic polaron is known as ferron, and it was described decades ago^{32,35}. In the whole range of J_{pd}' values there is no considerable difference between the 1D and 2D cases.

The spin structure of a ferron localized on two local spins is complex. The correlator of the carrier spin $\mathbf{s}$ with the two local AF spins $\mathbf{S}_p$, $\langle \mathbf{s}\mathbf{S}_p \rangle$, is negative (for antiferromagnetic p - d coupling) for the whole range of J_{pd}' . For a weak J_{pd}' , $\langle \mathbf{s}\mathbf{S}_p \rangle$ increases linearly, then saturates for very large J_{pd}' approaching -0.5 . The sharper increase of E_{ex} , which is seen for $J_{pd}' \cong 2.5$ is caused by a spin-flip of the two local spins, $\mathbf{S}_p$. The systematic increase of E_{ex} , faster than the linear increase, for $J_{pd}' > 4$ originates neither from the correlation $\langle \mathbf{s}\mathbf{S}_p \rangle$ nor from the correlation between two local spins $\langle \mathbf{S}_{p1}\mathbf{S}_{p2} \rangle$ but results from a systematic reconstruction of the AF environment of the ferron. The correlation of each of the $\mathbf{S}_p$ with surrounding spins, $\mathbf{S}_i$, gradually decreases. Simultaneously, there appears a reconstruction of d - d couplings among the surrounding spins.




FIG. 4: The correlator between the carrier spin and one of AF spin $\langle \mathbf{s}\mathbf{S}_i \rangle$ (a), the total spin moment of the AFP polaron, S_{iz}^{tot} , (b), and the correlator between two nearest AF spins $\langle \mathbf{S}_i \mathbf{S}_{i+1} \rangle$ (c) as a function of J'_{pd} for a homogeneously distributed trial function. The case of a 1D chain of 16 spins with PBC is presented by circles, the 2D 4×4 square with PBC is shown by open stars.

More apparent data about the mechanism of the formation of a ferron can be found if one assumes a homogeneous distribution of the carrier on the whole AF cluster with PBC. The data are shown in Fig. 4. The correlator between one of the AF spins and the carrier spin as a function of J'_{pd} is presented in Fig. 4a. The step-like behavior of $\langle \mathbf{s}\mathbf{S}_i \rangle$ is visible for both 1D and 2D cases. For $J'_{pd} < 2.5$ correlator $\langle \mathbf{s}\mathbf{S}_i \rangle = 0$ and $E_{ex} = 0$. For $J'_{pd} > 2.5$ E_{ex} increases in accordance with the observed steps of $\langle \mathbf{s}\mathbf{S}_i \rangle$. In Fig. 4b the total magnetic moment of the polaron, $S_{iz}^{tot} = \sum_i S_{iz} + s_z$ is presented. It is also characterized by steps occurring for the same values of J'_{pd} as those of $\langle \mathbf{s}\mathbf{S}_i \rangle$ when J'_{pd} is large. For $J'_{pd} < 9$ and 2D case the total magnetic moment is equal to $1/2$. For $J'_{pd} < 2.5$ this moment is located at the carrier, for $J'_{pd} > 2.5$ it is a result of the coupling of the electron spin ($s_z = 1/2$) with $\sum_i S_{iz} = 1$ AF spin. The correlator between two neighbor AF spins $\langle \mathbf{S}_i \mathbf{S}_{i+1} \rangle$ is presented in Fig. 4c. It changes from -0.4 for a pure AF to 0.25 (both spins parallel) with an increase in the strength of p - d coupling. At the same time, S_{iz}^{tot} approaches value 7.5 (all bonds broken). It is worth to note that the step-like behavior of $\langle \mathbf{S}_i \mathbf{S}_{i+1} \rangle$ is not a consequence of breaking of the subsequent bonds, but it is associated with steps of the total magnetic moment of the system.

To summarize, the ferron can form when homogeneous, Curie-Weiss magnetization is induced. Our re-




FIG. 5: (a) The mean value of the correlator between the carrier spin $\mathbf{s}$ and the spins of the AF sublattice on which the polaron is acting $\mathbf{S}_A$, $|\langle \mathbf{s}\mathbf{S}_A \rangle|$ (open circles), and the spins of other sublattice $\mathbf{S}_B$, $\langle \mathbf{s}\mathbf{S}_B \rangle$ (filled squares) as a function of J'_{pd} for a comb-like trial function. (b) The z -component of the carrier spin, s_z (filled squares), the central spin S_{0z} (open triangles), as well as the sum of AF spins $\sum_i S_{iz}$ (filled circles) for an open chain of 16 spins as a function of J'_{pd} . (c) The correlator between the spins from the same sublattice $\langle \mathbf{S}_i \mathbf{S}_{i+2} \rangle$ (filled circles) and from two neighbor sublattices $|\langle \mathbf{S}_i \mathbf{S}_{i+1} \rangle|$ (open squares) as a function of J'_{pd} .

sults complete well the classical model of ferron.

E. Comb-Like AFP

A homogeneous distribution of the carrier on many AF spins makes the E_{ex} on opposite spins cancel each other out. Thus we introduced a carrier trial function which is distributed on one of the Neel sublattices only as intuitively energetically favorable. The carrier distribution is described as follows:

$$|\varphi(i)|^2 = f(\mathbf{r}_i) \cos^2\left(\frac{\pi}{2a}\mathbf{r}_i\right), \quad (14)$$

where $f(\mathbf{r}_i)$ is an envelope function, usually Gaussian. We call such a polaron comb-like AFP^{25,33}.

E_{ex} versus J'_{pd} for the comb-like polaron with a Gaussian envelope function is presented by triangles in Fig. 1. For a small r'_p , the comb-like AFP is equivalent to the small AFP. For a bigger r'_p , the gain E_{ex} decreases, but it is still much greater than that for large AFP. E_{ex} for a large comb-like AFP is only three times smaller than that of a small AFP. This stems from a decrease of quantum fluctuations (see part IIIF).

The comb-like AFP induces a staggered magnetization in the AF medium. This is shown in Fig. 5a, where the mean value of the correlator between the carrier spin $\mathbf{s}$ and the spins of the AF sublattice on which the polaron is acting $\mathbf{S}_A$, $|\langle \mathbf{s}\mathbf{S}_A \rangle|$, and the spins of other sublattice $\mathbf{S}_B$, $\langle \mathbf{s}\mathbf{S}_B \rangle$, are presented by circles and squares, respectively. The values of the correlators increase linearly for small p - d coupling, and they saturate when $J'_{pd} > 1$. The saturation value for $\langle \mathbf{s}\mathbf{S}_B \rangle = 0.25$ and it is independent of the number of spins. The saturation value of $|\langle \mathbf{s}\mathbf{S}_A \rangle| > 0.25$ and depends on the number of spins. The difference between the magnetization of the A and B sublattices gives the net magnetic moment of AF.

A part of the magnetic moment which is transferred from the carrier to the AF medium depends on J'_{pd} , as it is shown in Fig. 5b. Here the change versus J'_{pd} of z -components of the carrier spin, s_z , of one of the spins on which the carrier acts, S_{0z} , and of the total spin, $\sum_i S_{iz}$, is presented. For small values of p - d coupling a quadratic increase of the moment transferred to AF is observed. $\sum_i S_{iz}$ saturates at a value smaller than 0.5. Simultaneously, the z -component of the carrier spin decreases from 0.5 for weak p - d coupling to the saturation value of 0.15 for an AF cluster consisting of 16 spins. However, $s_z + \sum_i S_{iz} = 0.5$ is independent on J'_{pd} .

The presence of the comb-like AFP on one of the Neel sublattices breaks the translation symmetry and leads to the formation of two magnetized sublattices. In Fig. 5c the correlators between NN, $|\langle \mathbf{S}_i \mathbf{S}_{i+1} \rangle|$, and NNN, $\langle \mathbf{S}_i \mathbf{S}_{i+2} \rangle$, are presented as a function of J'_{pd} . While $|\langle \mathbf{S}_i \mathbf{S}_{i+1} \rangle|$ decreases for large J'_{pd} , the correlator $\langle \mathbf{S}_i \mathbf{S}_{i+2} \rangle$ increases. Thus, a comb-like AFP increases the AF correlation radius. In the limit of very large J'_{pd} and not too small sizes of the AF cluster, the comb-like AFP transforms the quantum antiferromagnet into a classical one.

Although E_{ex} for the comb-like AFP is large, the probability of its formation is small because it is characterized by a big kinetic energy. Moreover, the comb-like AFP has a tendency to localize into small AFP. This comes from the fact that the kinetic energy is almost the same for both types of polarons (as long as only t_1 is taken into account) while E_{ex} due to quantum fluctuations increases three times with localization.

F. Quantum effects

In this section we summarize the results concerning the formation mechanisms of different magnetic polarons. We pay particular attention to the appearance of quantum effects. In paragraphs A-E, five types of antiferromagnetic polarons were presented. The forma-

tion of weak small, medium, and comb-like polarons is associated with the induction of staggered magnetization. In contrast, the formation of a strong ZR polaron is caused by the compensation of the AF spin by the carrier spin. The mechanism of ferron formation is the breaking of AF bonds, which is equivalent to the induction of a homogeneous moment.

Classically, the only possible mechanism of AF polaron formation at zero temperature is the turning of the spins in the direction of the effective field induced by the carrier spin^{32,35}. However, this mechanism does not explain the formation of the remaining polarons. The induction of staggered magnetization is directly associated with the quantum treatment of the AF. In a quantum approach the ground state of AF is a combination of Neel states, hence no sublattice is distinguished. The simplest measure of AF quantum fluctuations is the difference between the ground and the first excited states, which are both composed of Neel states. In the presence of staggered magnetization the Neel sublattices are distinguishable and the damping of spin fluctuations occurs³⁶.

The mechanism of compensation responsible for the formation of the ZR polaron should be also considered in a quantum approach. Classically, the carrier couples the AF spin and such interaction does not destroy the AF order. As we have shown in Fig. 3c, in the quantum treatment of the antiferromagnet the affected AF spin may cease to be correlated with neighbor spins. It means that only the quantum approach allows to model the destruction of antiferromagnetic order which is observed in experiments³⁷. Despite the quantum character of the discussed above mechanisms, there are some particular situations where the polarons can be described in the classical limit, but the quantum corrections have to be taken into account. These corrections are the result of scaling of spin fluctuations with the number of spins and seem to be important for the antiferromagnetic sign of J'_{pd} . By a systematic analysis of the dependence of E_{ex} on p - d coupling in the range of very large J'_{pd} , we have found that $E_{ex} = \sum_i j_{pd}(i) \langle \mathbf{s}\mathbf{S}_i \rangle$, where the summation is taken over the N spins $\mathbf{S}_i$ within the polaron size (see Fig. 2). The correlator depends on N and is equal to $\langle \mathbf{s}\mathbf{S}_i \rangle = (0.25 + 1/2N)$. Thus E_{ex} changes from $0.75J'_{pd}$ for a polaron localized on one spin to $0.25J'_{pd}$ for a polaron interacting with an infinite number of spins. Hence, it is possible to calculate the energy of strong small polarons as well as ferrons classically, but the appropriate scalar spin multiplication (0.25) has to be replaced by the quantum factor. It approaches the classical value when $N \rightarrow \infty$, whereas for $N = 1$ it is three times bigger. The same quantum factor 3 is lost when the ZR polaron is delocalized on one of the Neel sub-

lattices forming the comb-like polaron.

The importance of the sign of the p - d coupling is shown in the inset to Fig. 2. Here E_{ex} for a small AFP with either a positive or negative sign of J'_{pd} is presented. Different slopes of E_{ex} for ferro- and antiferromagnetic coupling are observed. It is a consequence of the fact that the carrier and AF spins can not couple ferromagnetically to more than 0.25 while for antiferromagnetic coupling $\langle \mathbf{sS}_i \rangle$ approaches -0.75 . Thus, only for antiferromagnetic coupling the corrections associated with the number of spins in the AF system are important. In the case of ferromagnetic coupling, the classical energy calculations for small polarons and ferrons are correct.

G. Polaron mass

In our approach (see Eq.(2)) we assume a simple decoupling of the carrier kinetic energy and the spin degree of freedom. For all the types of polarons discussed, the minimum energy corresponds to the localization of the maximum of the trial function, $\Psi(\mathbf{r})$, exactly at the position of the local spin $\mathbf{r}_0$. But another equivalent minima correspond to the localization at another equivalent spin positions. For PBC, which simulate the translation symmetry, all minima are exactly equivalent. As the consequence, the linear combination of the simplified solutions is expected to be a better solution of the problem. It shows that the carrier motion and the spin structure are really coupled. To study that problem correctly one should, however, diagonalize N times bigger matrixes. Anyway, our simplified approach gives a reasonable picture of the spin structure of a magnetic polaron under assumption of its static nature, but it does not allow to study the real correlation of the carrier motion and spin dynamics and does not bring any solid answer on the problem of the polaron localization. However, a hint about the effective polaron mass and the reduction of the kinetic energy can be found within our simple approach through the analysis of the change of the spin structure which accompanies the transfer of the polaron to the NN. When the decoupling of the motion and spin is assumed (Eq. (2)), the kinetic energy is described by the parameter t_1 , according to Eq. (6). Here, only the transfer without any spin flip is considered. Our solutions show, however, that the transfer is accompanied with a complex change of the spin structure. The spin structure of the surrounding local spins is very different when the carrier is localized on the first, A, or on the neighboring site, B. A posteriori, we are able to claim that the matrix elements describing the kinetic energy are reduced by a factor resulting from the product of the spin states on the site A and

B $\langle X_S^A | X_S^B \rangle$, respectively. In other words, to consider the effects which are omitted due to our assumption (Eq.(2)), one has to reduce the value of the parameter of the kinetic energy. Instead of t_1 as effective kinetic energy, $t_1^* = t_1 \langle X_S^A | X_S^B \rangle$ should be used. Our numerical study shows that for weak p - d coupling, $J_{pd} \ll J_{dd}$, the factor $\langle X_S^A | X_S^B \rangle$ is close to unity. For $J_{pd} \approx J_{dd}$ the value of $\langle X_S^A | X_S^B \rangle$ decreases, and for $J_{pd} > J_{dd}$ it saturates at the value in the range 0.1 - 0.2, depending on the type of polaron. It shows that the effective mass of polaron dressed by the spin polarization is considerably bigger as compared to free polaron.

IV. PHASE DIAGRAM OF MAGNETIC POLARONS

Until now we have considered the E_{ex} from magnetic polarons formation and we have described the spin structure of various polarons. However, the total energy (exchange, phonon and kinetic one) should be taken into account to specify which type of polaron forms. In this section we consider the formation of a pure magnetic polaron.




FIG. 6: Total energy, E_{tot} , as a function of polaron radius r'_p for $J'_{pd} = 1.875$ and effective masses of m_e (triangles), $2m_e$ (circles), $25m_e$ (squares).

In Fig. 6 the total energy (sum of kinetic and exchange energies) as a function of polaron radius calculated for a few chosen effective masses is shown for a 2D square cluster with PBC. It can be seen that for $m_{eff} = m_e$ no AFP can form. For a large m_{eff} (which scales as $1/t_1$), the only polaron which can exist is the small one. The formation of a ferron is not possible because J'_{pd} is too small. The medium and large polarons tend to localize in one elementary cell, independently of the values of m_{eff} and t_1 . The tendency to localization is associated with a rapid reduction of E_{ex} with increasing r'_p , which stems from quantum fluctu-

ations of the AF medium (see part IIIF). We found that for $J'_{pd} = 1.875$ magnetic polarons can form only if $m_{eff} > 1.6m_e$, what corresponds to $t_1 = 2J_{dd}$. For weaker p - d couplings the small AFP is also the only polaron which can form but its m_{eff} should be much greater.

In Fig. 7 the phase diagram of the formation of different magnetic polarons is shown. The area of parameters t_1 and J'_{pd} for which the small AFP forms is marked by a solid line.




FIG. 7: Phase diagram of magnetic polaron formation. In the inset E_{tot} as a function of t_1 for $J'_{pd} = 4.4$ is shown. In the inset dashed line presents $E_{tot}(t_1)$ for two-spin ferron, the solid line shows $E_{tot}(t_1)$ for small AFP. Vertical lines separate the areas of different polarons formation

For higher J'_{pd} , the small ferrons can also form. In the inset to Fig. 7 the total energies of a small AFP and a small ferron are compared for $J'_{pd} = 4.4$. E_{ex} for a small AFP is higher than for the two spin ferron, and it is constant. The kinetic energy of two-spin ferron (polaron localized on two neighboring spins) is smaller than that of a small AFP and scales linearly with t_1 . Thus the total energies of both polarons are linear functions of t_1 but with different slopes. In particular the boundary between small AFP and two spin ferron for $J'_{pd} = 4.4$ crosses for $t_1 = 5.4J_{dd}$, what is equivalent to $m_{eff} \geq 0.6m_e$. For t_1 , which is greater than $6.25J_{dd}$ any AFP is not formed. In general, the small AFP forms for $m_{eff} \geq m_e$, while the two-spin ferron appears for $m_{eff} < m_e$.

Similarly, we found the range of parameters for which other types of polarons can also form. In Fig. 7 the ranges where small AFP, two, four-spin ferrons can occur are shaded by solid, dotted and dashed lines, respectively. The appearance of a three-spin ferron is indicated by rectangles. Larger ferrons appear for much stronger p - d couplings, and we omit their description because they would exist for nonphysical parameters.

The presented results were calculated for a 2D square

with PBC. To estimate the error caused by small size of antiferromagnetic cluster, we investigated also such clusters as: a 4×4 square without PBC, a 4×4 parallelogram, and $2 \times N$ systems where $2 \leq N \leq 10$. We found that the energy of polarons with small size depends on the nearest vicinity only. It is weakly dependent on both N and boundary conditions. For different 2D clusters the formation range of subsequent polarons can be shifted about 10%–15%.

The investigation of polaron formation in a wide range of parameters is exceptionally valuable when we want to classify what type of polaron could be formed in different materials. For example, in doped EuTe where $J_{pd} \approx 0.125$ eV and $J_{dd} \approx 2$ meV³⁸ the p - d coupling on one AF bonds $J'_{pd} \approx 8$. At the same time, $t_1 \approx 15J_{dd}$. For such parameters our model predicts the ferrons formation (see Fig. 7) in accord with experiments (see^{32,38} and references therein).

In high- T_c superconductors which are based on CuO_2 layers, the d - d exchange coupling ranges from 0.055 eV to 0.085 eV, as determined from the Neel temperature of antiferromagnetic precursors of these materials³⁹. $J_{pd} \approx 1 - 3$ eV was determined from the band structure calculations^{23,40,41,42}. Thus, the ratio of p - d to d - d exchange energies is between 1.5 and 4 for $J_{dd} = 0.075$ eV. m_{eff} is much more difficult to determine because the mass observed in experiments (e.g. in ARPES) is decorated by phonon and exchange interactions. Since the decorated m_{eff} observed in ARPES experiments⁴³ is about $4m_e$ and m_{eff} in our model is dressed only by phonons, the m_{eff} which should be considered in the phase diagram is smaller than $4m_e$, which is equivalent to $t_1 > 0.8J_{dd}$.

We conclude on the basis of our phase diagram that for parameters typical for weakly doped high- T_c superconductors mainly the small AFP would form. There may be also some competition between the formation of small AFP and two-spin ferrons provided that the effective mass dressed in phonons is a bit lower than the electron mass. Large AFP have energies of few orders of magnitude lower than those of small AFP and ferrons.

V. THE CONTRIBUTION OF PHONON AND MAGNETIC POLARON

Now we will compare the phonon and magnetic contributions to the formation of polarons in weakly doped high- T_c superconductors. We have shown that in the 2D case E_{ex} from the formation of large magnetic polarons is close to zero and that they are unlikely to form (Fig. 6 and Fig. 7). Mott and Alexandrov¹⁰ suggest that in high- T_c superconductors only small phonon polarons




FIG. 8: E_{ex} from the formation of a small AFP as a function of J'_{pd} (a). The phonon energy, E_{ph} , versus effective dielectric constant κ (b). The absolute value of the total energy for a magnetic polaron (circles) and for a phonon polaron (solid line) as a function of J'_{pd} (c). Here, $m_{eff} = 2.2m_e$ and $\kappa = 5$. The vertical dashed line shows the value of J'_{pd} where the magnetic and phonon polaron energies are equal.

form (see Eq. (12)). Thus we will not consider large polarons here, neither of magnetic nor phonon origin.

In Fig. 8a, E_{ex} due to the formation of a small magnetic polaron in a 2D AF square with PBC is shown as a function of J'_{pd} . In Fig. 8b, the energy gain due to the formation of phonon polaron is presented as a function of effective dielectric constant κ . Typical values of κ are between 5 and 20. The kinetic energy for both small polarons is the same, $E_k = 4|t_1|$, and is omitted for clarity.

Horizontal and vertical dotted lines drawn in Figs. 8a and 8b indicate parameters $J'_{pd} = 1$ and $\kappa = 10$ for which energy gain $E_{ex} = E_{ph} = 0.35$ eV is the same for both phonon and magnetic polarons. The energy gain due to the formation of phonon polarons is greater than that for magnetic polarons for $\kappa < 10$ and $J'_{pd} < 1$, while $\kappa > 10$ and $J'_{pd} > 1$ the magnetic polaron dominates. One can see that for the range of parameters, which seem to be typical for high- T_c superconductors, the energy gain due to the formation of phonon and magnetic polarons is comparable and of the order of fraction of eV.

In order to obtain the total energy of magnetic and phonon polaron separately, E_{tot} , we have evaluated the energies for a chosen set of parameters: $m_{eff} = 2.2m_e$ and $\kappa = 5$. This mass, according to ARPES experiments⁴³ and band structure calculations⁴⁰, is reasonable for high- T_c superconductors. κ is taken from theory of phonon polaron¹⁰. In Fig. 8c, we show the values of E_{tot} for phonon as well as magnetic polarons versus J'_{pd} . For the phonon polaron E_{tot} is constant and equal to 0.15 eV since the phonon as well as kinetic energies are independent of J'_{pd} . The phonon polaron dominates in the range of weak p - d couplings. In contrast, the magnetic polaron (circles in Fig. 8c) dominates in the range of strong J'_{pd} where its energy increases linearly with J'_{pd} . In the range of $J'_{pd} = 1.5 - 4$, which is typical for weakly doped high- T_c superconductors, the energies of both polarons are comparable or magnetic polaron energy slightly overcomes the energy of phonon one. This result agrees well with a very recent paper⁴⁴ which stresses the importance of phonon interactions in high- T_c superconductors.

We conclude that within our model the phonon and magnetic polaron energies are comparable and that both contributions should be included in the total polaron energy in high- T_c superconductors.

VI. SUMMARY

Using the spin-fermion model and treating all spins in quantum approach, we found that depending on the material parameters five various types of magnetic polarons in antiferromagnetic medium can be distinguished.

We showed that in the range of parameters typical for weakly doped high- T_c superconductors the contributions of phonon and magnetic interactions to the formation of a polaron are comparable and hybrid magnetic-phonon polarons form.

In weakly doped high- T_c superconductors small magnetic polarons as well as small ferrons can form. Our numerical study allows to find a continuous evolution from Zhang-Rice approach, when p - d coupling is assumed to be much stronger than d - d coupling, via important for high- T_c materials intermediate range, to linear response approach suitable for weak p - d coupling.

The here introduced comb-like polarons cannot form when the band is empty (i.e. in undoped material) because of the cost of high kinetic energy. However, they can play a fundamental role in doped high- T_c materials when the band is partially filled^{25,33}.

ACKNOWLEDGEMENTS

Valuable discussion with H. Przybylińska. Work supported by the KBN grant 2 P03B 007 16.

-
- ¹ M. K. Crawford, M. N. Kunchur, W. E. Farneth, E. M. McCaron, and S. J. Poon, Phys. Rev. B **41**, 282 (1990).
 - ² J. P. Franck, J. Jung, M. A.-K. Mohamed, S. Gyga, and G. I. Spoule, Phys. Rev. B **44**, 5318 (1991).
 - ³ M. R. Norman, H. Ding, M. Randeria, J. C. Campuzano, T. Yokoya, T. Takahashi, T. Mochiku, K. Kadowaki, P. Guptasarma, and D. G. Hinks, Nature **392**, 157 (2000).
 - ⁴ K. Karpińska, M. Z. Cieplak, S. Guha, A. Malinowski, T. Skośkiewicz, W. Plesiewicz, M. Berkowski, B. Boyce, T. R. Lemberger, and P. Lindendorf, Phys. Rev. Lett. **84**, 155 (2000).
 - ⁵ B. G. Levi, Phys. Today **17**, 53 (2000).
 - ⁶ C. Castellani, C. D. Castro, and M. Grilli, Phys. Rev. Lett. **75**, 4650 (1995).
 - ⁷ S. I. Pekar, Zh. Eksp. Teor. Fiz. **16**, 335 (1951).
 - ⁸ H. Fröhlich, Phys. Rev. **79**, 845 (1954).
 - ⁹ H. Fröhlich, Adv. Phys. **3**, 325 (1954).
 - ¹⁰ A. S. Alexandrov and N. Mott, *Polarons and Bipolarons* (World Scientific, Singapore, 1995).
 - ¹¹ A. S. Alexandrov, Phys. Rev. B **38**, 925 (1988).
 - ¹² A. Millis, H. Monien, and D. Pines, Phys. Rev. B **43**, 258 (1991).
 - ¹³ F. C. Zhang and T. M. Rice, Phys. Rev. B **37**, 3759 (1988).
 - ¹⁴ E. Dagotto, Rev. Mod. Phys. **66**, 763 (1994).
 - ¹⁵ S. R. White and D. J. Scalapino, Phys. Rev. Lett. **84**, 3021 (2000).
 - ¹⁶ C. Hellberg and E. Manousakis, Phys. Rev. Lett. **84**, 3022 (2000).
 - ¹⁷ S. Schmitt-Rink, C. Varma, and A. E. Ruckenstein, Phys. Rev. Lett. **60**, 2793 (1988).
 - ¹⁸ C. L. Kane, P. Lee, and N. Read, Phys. Rev. B **39**, 6880 (1989).
 - ¹⁹ V. Elser, D. A. Huse, B. I. Shraiman, and E. D. Siggia, Phys. Rev. B **41**, 6715 (1990).
 - ²⁰ A. Ramsak and P. Horsch, Phys. Rev. B **48**, 10559 (1993).
 - ²¹ G. F. Reiter, Phys. Rev. B **49**, 1536 (1994).
 - ²² Z. Liu and E. Manousakis, Phys. Rev. B **45**, 2425 (1992).
 - ²³ C. Buhler, S. Yunoki, and A. Moreo, Phys. Rev. Lett. **84**, 2690 (2000).
 - ²⁴ B. L. Altshuler, L. B. Ioffe, and A. J. Millis, Phys. Rev. B **52**, 5563 (1995).
 - ²⁵ E. M. Hankiewicz, R. Buczko, and Z. Wilamowski, Physica B **284-288**, 437 (2000).
 - ²⁶ J. R. Schrieffer, J. Low Temp. Phys. **99**, 397 (1995).
 - ²⁷ A. Ramsak and P. Prelovsek, Phys. Rev. B **42**, 10415 (1990).
 - ²⁸ M. Hamada and H. Shimahara, Phys. Rev. B **51**, 3027 (1995).
 - ²⁹ J. Bała, A. M. Oleś, and J. Zaanen, Phys. Rev. B **54**, 10161 (1996).
 - ³⁰ J. Bała and A. M. Oleś, Phys. Rev. B **61**, 6907 (2000).
 - ³¹ J. J. M. Poethuizen, R. Eder, N. T. Hien, M. Matoba, A. A. Menovsky, and G. A. Sawatzky, Phys. Rev. B **78**, 717 (1997).
 - ³² T. Kasuya and A. Yanase, Rev. Mod. Phys. **40**, 684 (1968).
 - ³³ E. M. Hankiewicz, R. Buczko, and Z. Wilamowski, Acta Phys. Polonica A **97**, 185 (2000).
 - ³⁴ M. Laukamp, G. B. Martins, C. Gazza, A. L. Malvezzi, E. Dagotto, P. M. Hansen, and A. C. L. J. Riera, Phys. Rev. B **57**, 10755 (1998).
 - ³⁵ V. D. Lakhno and E. Nagaev, Fiz. Tverdogo Tela **18**, 3429 (1976).
 - ³⁶ Z. Wilamowski and E. M. Hankiewicz, Acta Phys. Polonica A **97**, 403 (2000).
 - ³⁷ R. J. Birgeneau, D. R. Gabbe, H. P. Jenssen, M. A. Kastner, P. J. Picone, T. R. Thurston, G. Shirane, Y. Endo, M. Sato, K. Yamada, et al., Phys. Rev. B **38**, 6614 (1988).
 - ³⁸ P. Wachter, in *Handbook on the Physics and Chemistry of the Rare Earths* (1979), p. 507, eds. K. A. Geschneider, Jr. and L. Eyring.
 - ³⁹ N. M. Plakida, *High Temperature Superconductivity* (Springer Verlag, Berlin, 1995).
 - ⁴⁰ M. S. Hybertsen, E. B. Stechel, M. Schluter, and D. Jennison, Phys. Rev. B **41**, 11068 (1990).
 - ⁴¹ H. Eskes, L. H. Tjeng, and G. Sawatzky, Phys. Rev. B **41**, 288 (1990).
 - ⁴² C. X. Chen, H. B. Schüttler, and A. J. Fredro, Phys. Rev. B **41**, 2581 (1990).
 - ⁴³ G. Mante, R. Claessen, T. Buslaps, S. Harmand, R. Manzke, and M. S. J. Fink, Z. Phys. B **80**, 181 (1990).
 - ⁴⁴ A. Lanzara, P. V. Bogdanov, X. J. Zhou, S. A. Kellar, D. L. Feng, E. D. Lu, T. Yoshida, H. Eisaki, A. Fujimori, K. Kishio, et al., Nature **412**, 510 (2001).